

Hydromite 100

PRODUCT INFORMATION BROCHURE

Hydromite 100 is a booster sensitive emulsion explosive which is produced on site by sensitizing an emulsion matrix by chemical gassing. Hydromite 100 is pumped directly into the borehole by an approved pump truck or pump unit.

ADVANTAGES

- Excellent water resistance
- Very low amount of toxic fumes
- Very low sensitivity against mechanical and thermal stress
- Very good filling of the boreholes
- Suitable for underground use

PROPERTIES

Properties	Value
Density [g/cm ³]	1.05 – 1.15
Oxygen balance [%] ⁽¹⁾	-0.8
Gas Volume [L/kg] ⁽¹⁾	958
Heat of explosion [kJ/kg] ⁽¹⁾	2,937
Relative weight strength [ANFO=100] ⁽¹⁾	76
Relative bulk strength [ANFO=0.85 g/cm ³] ⁽¹⁾	98
Velocity of detonation [m/s] (confined) ⁽²⁾	4,000

Notes:

⁽¹⁾ Theoretical values based on Austin modeling which assumes ideal detonation. Values calculated with other codes may differ.

⁽²⁾ The velocity of detonation will depend on application, diameter and confinement.



AUSTIN POWDER

Austin Powder Malaysia Sdn. Bhd.

(Registration No.: 197601000224) (26191-A)
(Formerly known as Tenaga Kimia Sdn Bhd)

No. 8, Jalan SS 22/21, Damansara Jaya, 47400 Petaling Jaya, Selangor Darul Ehsan. Tel : 603 - 7729 7464 | Fax : 603 - 7729 8383

Hydromite 100

PRODUCT INFORMATION BROCHURE

USE

- Lower temperature limit +5°C
- Upper temperature limit +50°C
- Minimum booster APB 20 or emulsion explosive (e.g. Emulex 1)
- Minimum borehole diameter 35 mm
- Not for use in hazardous environments where flammable gases or dust may exist
- Maximum static overpressure 3 bar (0.3 MPa)
- Austin accepts no responsibility for any loss or liability arising from use of the product in ground containing pyritic or other reactive material

SHELF LIFE

Maximum 48 hours from production in the borehole



Contact your local Austin Powder representative for further information.

Disclaimer of Warranties and Limitations of Liabilities

The data set forth in this Product Information Brochure (PIB) are based on the product test procedures of Tenaga Kimia Sdn Bhd in use at the time of publication of this PIB. Specifications, test values and information are exclusively non-binding preliminary information and are not guaranteed; the actual data may differ for various reasons (e.g. temperature, humidity, pressure). Technical inaccuracies or typographical errors and the right to amend the PIB at any time without notice shall be reserved. Tenaga Kimia Sdn Bhd, its subsidiaries and distributors do not assume any liability, covenants, guaranties or warranties with respect to the completeness, accuracy, reliability, suitability or availability of the product and the information of the PIB. Any liability for damages of any kind (such as direct or indirect, incidental or consequential damages, losses or expenses), directly or indirectly related for any reason to this PIB or the use of the products is excluded. The customer is (even when making decisions based on the information in the PIB) solely responsible for the proper use of the potentially dangerous products that, accordingly, may only be used by trained personnel and in compliance with applicable law. To the entire legal relationship between their customers and Tenaga Kimia Sdn Bhd their (TKSB) general terms and conditions (please refer to standard terms of sale) shall apply.



AUSTIN POWDER

Austin Powder Malaysia Sdn. Bhd.

(Registration No.: 197601000224) (26191-A)
(Formerly known as Tenaga Kimia Sdn Bhd)

No. 8, Jalan SS 22/21, Damansara Jaya, 47400 Petaling Jaya, Selangor Darul Ehsan. Tel : 603 - 7729 7464 | Fax : 603 - 7729 8383

02/2020